


DELPHION

No active tr

Select CR**RESEARCH****PRODUCTS****INSIDE DELPHION****Log Out** **Work Files** **Saved Searches****My Account**

Search: Quick/Number Boolean Advanced Der

The Delphion Integrated ViewGet Now: ☒ **PDF** | [File History](#) | [Other choices](#)Tools: Add to Work File: [Create new Work](#)View: **INPADOC** | Jump to: **Top** Go to: [Derwent](#) [Ema](#)? Title: **JP02111883A2: ELECTROLESS METAL PLATING METHOD**? Derwent Title: Electroless metal plating for high density coating - involves adsorbing reducing agent on substrate, dipping in soln. contg. catalytic metal ions, etc. [[Derwent Record](#)]? Country: **JP Japan**? Kind: **A**? Inventor: **MATSUI TOSHIKI;
IMAI TOMOYUKI;
FUKUKAITO MASAOKI;
HORIISHI NANAOKI;**? Assignee: **TODA KOGYO CORP**
[News, Profiles, Stocks and More about this company](#)? Published / Filed: **1990-04-24 / 1988-10-20**? Application
Number: **JP1988000265711**? IPC Code: Advanced: **C23C 18/28; C23C 18/36;**
Core: **C23C 18/20; C23C 18/31;**
IPC-7: **C23C 18/28;**
C23C 18/36;? Priority Number: **1988-10-20 JP1988000265711**? Abstract: **PURPOSE:** To form a uniform dense metal plating film having satisfactory adhesion without using a noble metal catalyst by adsorbing a reducing agent on a body to be plated, immersing the body in a soln. contg. ions of a self-catalytic metal, reducing the deposited metal and carrying out electroless plating.**CONSTITUTION:** A reducing agent such as an aq. soln. of sodium borohydride is adsorbed on a body to be plated. This body is immersed in an aq. soln. contg. ions of a self-catalytic metal such as Ni, Co or Cu to deposit the metal and the deposited metal is reduced with the reducing agent. The body to be plated is then electroless-plated with a metal such as Ni, Co or Cu. A uniform dense plating film having superior adhesion can be formed without using an expensive noble metal catalyst.**COPYRIGHT:** (C)1990,JPO&JapioFamily: **None**Other Abstract **DERABS C90-169179 DERC90-169179**
Info: